



Cement Mill Test Report

Month of Issue: July 2024

Plant: Harleyville, South Carolina
Product: Portland Cement Type III
Silo: 6, 9
Manufactured: June 2024

ASTM C150 and AASHTO M 85 Standard Requirements

CHEMICAL ANALYSIS			PHYSICAL ANALYSIS		
Item	Spec limit	Test Result	Item	Spec limit	Test Result
Rapid Method, X-Ray (C114)			Air content of mortar (%) (C185)		
SiO ₂ (%)	---	20.3		12 max	5
Al ₂ O ₃ (%)	---	4.7	Blaine Fineness (m ² /kg) (C204)		
Fe ₂ O ₃ (%)	---	3.5		---	504
CaO (%)	---	64.3	Fineness, No. 325 sieve, (% retained) (C430)		
MgO (%)	6.0 max	1.4		---	0.1
SO ₃ (%)	3.5 max †	2.5	Compressive strength (MPa, [PSI]) (C109)		
Loss on ignition (%)	3.0 max	1.5	1 day	12.0 [1740] min	21.9 [3180]
Insoluble residue (%) ‡	1.5 max	0.15	3 days	24.0 [3480] min	35.5 [5150]
Equivalent alkalis (%)	--- §	0.49	7 days	---	41.0 [5950]
			28 days (Reflects previous month's data)	---	49.7 [7200]
			Time of setting (minutes)		
Adjusted Potential Phase Composition (C150)			Vicat Initial (C191)	45 - 375	80
C3S (%)	---	64	Mortar Bar Expansion (%) (C1038) ‡		
C2S (%)	---	10		0.020 max	0.001
C4AF (%)	---	11			
ASTM C150 and AASHTO M 85 Optional Chemical Requirements:			ASTM C150 and AASHTO M 85 Optional Physical Requirements:		
C3A (%)	8 max	7	Early Stiffening(%)	50 min	59
Chloride (%) (for information only)	---	0.02			

* Dashes in the spec limit mean Not Applicable

† May exceed 3.5% SO₃ maximum based on our C1038 results of < 0.020% expansion at 14 days.

‡ Current production run not available - most recent provided.

§ Please refer to ASTM C1778 or AASHTO R 80 for guidance on reducing the risk of alkali aggregate reaction in concrete.

Analysts: Richard Buford, George Wren, Neil Graham

We certify that the above described cement, at the time of shipment, meets the chemical and physical requirements of applicable SCDOT, NCDOT, GDOT, MDOT, VDOT, TDOT Specifications for Type III CEMENT;
ASTM C150 & AASHTO M 85 STANDARD SPECIFICATIONS FOR TYPE III CEMENT;

Certified By:

Sean J. Makens - Quality Manager
Report created: 7/11/2024

Argos USA
Harleyville Plant
463 Judge Street, Harleyville, South Carolina 29448
Phone: 843-806-2244