



# Cement Mill Test Report

Month of Issue: July 2024

**Plant:** Atlanta, GA Plant  
**Product:** Masonry Cement Type N  
**Color:** White  
**Manufactured:** June 2024

## ASTM C91 Standard Requirements

Item	Spec limit	Test Result
Fineness, Residue retained on a 45 um sieve (%)	24 max	10
Time of setting, Gillmore method: Initial set, minutes	120 min 1000 max	230
Compressive strength (MPa, PSI) 7 days	3.4 (500)	10.3 (1500)
28 days (Reflects previous month's data)	6.2 (900)	13.4 (1950)
Air content of mortar (%)	8 min 21 max	18
Water Retention (% of original flow)	70 min	77

We certify that the above described cement, at the time of shipment, meets the requirements of ASTM C91.

Argos USA - Atlanta Plant  
2520 Paul Ave. NW 30318  
Phone: 404.792.6156

Certified B\*\*

Sonya Becknel - Quality Manager  
7/15/2024